



404-CR

Neoprene (Chloroprene) Sponge Grades

Temperature Range (depending on grade)

Constant Low:	-40°C	Intermittent Low:	-50°C
Constant High:	85°C	Intermittent High:	120°C

Produced from 100% neoprene polymer, most closed cell neoprene sponge products meet UL94HF-1 flame rating, some will even meet UL94V-0. Premium closed cell neoprene sponge products will resist light oil contact, ozone, alkalis and acids, making them a good choice for general enclosure door gaskets.

Our Ref	Density Kg/m ³	Shore	ASTM D 1056-68
04-144A2	144	50	2A2
04-144A3	144	60	2A3
04-145A2	145	53	2A2
04-145A3	145	55	2A3
04-195A2	195	-	2A2
04-208C1	208	33	2C1
04-240C1	240	24	2C1
04-254C2	254	50	2C2
04-308C2	308	70	2C3
04-360C2	360	80	2C2
04-384C5	384	70	2C5
04-458C5	458	80	2C5

Full data sheets for all grades are available on request.

t: +44 (0)1590 688022
f: +44 (0)1590 673055

e: enquiries@emiseals.com
w: www.emiseals.com

EMI Group, 370 Ampress Lane, Lymington,
Hampshire, SO41 8JX, England