



411 – NBR/PVC/CR Closed Cell Sponge Grades

Temperature Range (depending on grade)

Constant Low: -25°C
Constant High: +85°C

Intermittent Low: -40°C
Intermittent High: +93°C

These blends of closed cell sponge are versatile, having a temperature range of -40°C to 93°C, and have flame ratings of UL94V0 and UL94HF-1 depending on thickness. They tend to have slightly lower density than most closed cell sponge products, and the water absorption properties are slightly higher than closed cell Neoprene's.

Our Ref	Density Kg/m ³	Shore	ASTM D 1056-68
411-68C1	68	28	2C1
411-90B1/2	90	45	2B1/2
411-104B2	104	50	2B2
411-120B2/3	120	55	2B2/3
411-1300B1/2	130	50	2B1/2
411-132B3	132	73	2B3

Full data sheets for all grades are available on request.

The information above is supplied in good faith and believed to be correct. This information is supplied upon the condition that persons receiving this will make their own determination as to its suitability for their purposes prior to use. EMI makes no representations or warranties, either expressed or implied with respect to the information or the product to which this information refers.

t: +44 (0)1590 688022
f: +44 (0)1590 673055

e: enquiries@emiseals.com
w: www.emiseals.com

EMI Group, 370 Ampress Lane, Lymington,
Hampshire, SO41 8JX, England